

# WEARTECH® WT-6

## BARE CAST ROD

Cobalt ■ AWS A5.21 ERCoCr-A

### KEY FEATURES

- Cobalt, high chromium, tungsten
- Excellent for corrosion resistance, wear and galling
- Most flexible and widely used of the cobalt alloys due to overall performance
- Retains hardness up to 930°F (500°C)
- These key features are universal to all WT-6 product forms

### TYPICAL APPLICATIONS

- Shear Blades
- Fluid Flow Valves
- Extrusion Screws
- Roll Bushings
- High Temperature
- Valve Bearing Surface

### WELDING PROCESSES

- Gas Tungsten Arc Welding
- Oxyfuel Welding

### WELDING POSITIONS

- All

DIAMETER		PART NUMBER	ROD LENGTH	UNIT OF MEASURE
mm	in	Tube	915 mm (36 in)	5 kg (11.02 lb)
2.4	3/32	B1060-240X915	All part numbers shown will ship in 915 mm (36 in) length  *Additional lengths available upon request and lead times may vary.	Weartech product is priced and shipped as kilograms.  *Please contact our Customer Care team to verify conversion rates.
3.2	1/8	B1060-320X915		
4.0	5/32	B1060-400X915		
4.8	3/16	B1060-480X915		
6.4	1/4	B1060-640X915		
7.9	5/16	B1060-800X915		

### DEPOSIT COMPOSITION<sup>(1)</sup>

Requirements	%C	%Mn	%Si	%Cr	%Ni	%Fe	%Mo	%W	%Co	Hardness, Rc
AWS A5.21 ERCoCr-A	0.9-1.4	1.0 max	2.0 max	26-32	3.0 max	3.0 max	1.0 max	3.0 -6.0	Balance	Not Required
<b>Typical Results</b>	1.1	0.1	1.3	28.2	2.5	2.5	0.1	4.7	59	42

### TYPICAL OPERATING PROCEDURES

Polarity	3.2 mm (1/8 in)	Current (Amps) 4.0 mm (5/32 in)	4.8 mm (3/16 in)
DC-	115-135	145-165	175-195

<sup>(1)</sup>Composition and properties depend upon dilution. Single layer deposit properties depend upon base metal and/or build-up material. <sup>(2)</sup>Preferred polarity is listed first.

#### IMPORTANT: SPECIAL VENTILATION AND/OR EXHAUST REQUIRED

Fumes from the normal use of some welding products can contain significant quantities of components - such as chromium and manganese - which can lower the 5.0 mg/m<sup>3</sup> maximum exposure guideline for general welding fume.

BEFORE USE, READ AND UNDERSTAND THE SAFETY DATA SHEET (SDS) FOR THIS PRODUCT AND SPECIFIC INFORMATION PRINTED ON THE PRODUCT CONTAINER.

*Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at [www.lincolnelectric.com](http://www.lincolnelectric.com)*

#### TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

#### CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.com](http://www.lincolnelectric.com) for any updated information.